

# Specification of Thermoelectric Module

## TETC1-11908CH6

### Description

The 119 couples, 40mm x 40mm size single module is made of selected high performance ingot and fabricated by our unique “soft” processes to achieve superior cooling/heating performance, is good for frequently cooling and heating applications. It is designed for superior cooling and heating up to 100 °C applications. Beyond the standard below, we can design and manufacture the custom made module according to your special requirements.

### Features

- No moving parts, no noise, and solid-state
- Compact structure, small in size, light in weight
- Environmental friendly
- RoHS compliant
- Precise temperature control
- Exceptionally reliable in quality, high performance


### Application

- Food and beverage service refrigerator
- Portable cooler box for cars
- Liquid cooling
- Temperature stabilizer
- CPU cooler and scientific instrument
- Photonic and medical systems

### Performance Specification Sheet

Th (°C)	27	50	Hot side temperature at environment: dry air, N <sub>2</sub>
DT <sub>max</sub> (°C)	70	79	Temperature Difference between cold and hot side of the module when cooling capacity is zero at cold side
U <sub>max</sub> (Voltage)	15.0	16.1	Voltage applied to the module at DT <sub>max</sub>
I <sub>max</sub> (Amps)	8.2	8.2	DC current through the modules at DT <sub>max</sub>
Q <sub>Cmax</sub> (Watts)	76.9	84.1	Cooling capacity at cold side of the module under DT=0 °C
AC resistance (Ohms)	1.4	1.5	The module resistance is tested under AC
Tolerance (%)	± 10		For thermal and electricity parameters

### Geometric Characteristics Dimensions in millimeters



### Manufacturing Options

#### A. Solder:

1. T100: BiSn (T<sub>melt</sub>=138°C)
2. T200: CuAgSn (T<sub>melt</sub> = 217°C)
3. T240: SbSn (T<sub>melt</sub> = 240°C)

#### B. Sealant:

1. NS: No sealing (Standard)
2. SS: Silicone sealant
3. EPS: Epoxy sealant

#### C. Ceramics:

1. Alumina (Al<sub>2</sub>O<sub>3</sub>, white 96%)
2. Aluminum Nitride (AlN)

#### D. Ceramics Surface Options:

1. Blank ceramics (not metalized)
2. Metalized

### Ordering Option



Suffix	Thickness H (mm)	Flatness/ Parallelism (mm)	Lead wire length(mm) Standard/Optional length
TF	0:3.6± 0.1	0: 0.08/0.08	360±10/Specify

**Operation Cautions**



- Cold side of the module sticked on the object being cooled
- Hot side of the module mounted on a heat radiator
- Work under DC
- Operation below  $I_{max}$  or  $V_{max}$
- Operation or storage module below  $100\text{ }^{\circ}\text{C}$

**Performance Curves at  $T_h=27\text{ }^{\circ}\text{C}$**



**Performance Curves at  $T_h=50\text{ }^{\circ}\text{C}$**



Standard Performance Graph  $Q_c = f(DT)$




Standard Performance Graph  $V = f(DT)$




Standard Performance Graph  $Q_c = f(V)$



**Performance Curves at Th=27 °C**



**Performance Curves at Th=50 °C**



Standard Performance Graph COP = f(V) of DT ranged from 0 to 30 °C




Standard Performance Graph COP = f(V) of DT ranged from 40 to 60/70 °C


Remark: The coefficient of performance (COP) is the cooling power  $Q_c$ /Input power ( $V \times I$ ).

A typical 127 couples module is fabricated by the unique “soft” process and has demonstrated that it only has 2.5% degrading after 300,000 thermal cycling. The below graphic shows that in beginning 120,000 cycles, it degrade about 2.5%, and then go on stable with very tiny degrading in further 180,000 thermal cycles. It is derived out that the modules can go over million thermal cycles.

**TEC Thermal Cycle Lifetime Test On TETC1-12706**



Typical cooling-heating cycle



The Chart for AC Resistance and AC Resistance Changes

---

**Creative technology with fine manufacturing processes provides you the reliable and quality products.**

**Tel: +86-791-88198288 Fax: +86-791-88198308 Email: [info@thermonamic.com](mailto:info@thermonamic.com) Web Site: [www.thermonamic.com](http://www.thermonamic.com)**

**Tel: +86-592-5714012**

**Fax: +86-592-5714010**

**Email: [info@thermonamic.com](mailto:info@thermonamic.com)**

**<http://thermonamic.com/>**

---

**Creative technology with fine manufacturing processes provides you the reliable and quality products**

**Tel: +86-791-88198288 Fax: +86-791-88198308 Email: [info@thermonamic.com.cn](mailto:info@thermonamic.com.cn) Web Site: [www.thermonamic.com](http://www.thermonamic.com)**